



The One-Source Solutions Provider
DESIGN | FORMULATE | COMPOUND | MOLD | FINISH
Thermoset Composites

PROPERTIES		MB1000-	MB1000-	MB1000-	MB2000-	MB2000-	MB2000-	MB2000-	MB2000-	MB3000-	MB3000-	MB4000	MB5500	MB6000
		10	15	25	5	10	15	20	25	15NY	20NY			
Listed File E80533	-	No	Yes	No	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes	No
Flammability UL94	-	HB	HB	HB	V0	V0	V0	V0	V0	V0/5V	V0/5V	V0	V0	HB
MECHANICAL PROPERTIES														
Impact Strength, Notched Izod, J/m	D256	135-185	215-320	370-535	80-135	215-320	270-370	425-530	530-640	425-535	425-750	505-560	425-530	160-370
Flexural Strength, Mpa	D790	95-110	125-145	130-150	55-75	90-110	110-125	130-150	160-170	125-145	125-145	115-125	115-130	100-160
Flexural Modulus, Gpa	D790	13.8-15.1	11-12.4	10.3-11.7	9.0-11.0	9.0-11.0	10.3-12.4	11.7-13.8	10.3-11.7	12.4-13.1	12.4-13.1	11.7-13.1	11.0-12.5	11.0-15.1
Tensile Strength, Mpa	D638	50-70	50-60	50-70	25-35	30-35	40-50	35-55	55-70	35-40	40-60	60-70	40-55	35-60
Compressive Strength, Mpa	D695	105-125	125-150	140-165	95-110	120-30	125-145	140-165	140-170	95-110	95-110	145-165	90-10	-
Shear Strength, Mpa	D732	40-50	50-55	50-60	25-35	40-50	55-60	60-75	70-80	55-60	55-60	-	-	-
ELECTRICAL PROPERTIES														
Arc Resistance, Seconds	D495	180+	180+	140+	185+	185+	185+	185+	185+	185+	185+	185+	185+	-
Inclined-Plane Tracking, Minutes	D2303	500+	500+	500+	1000+	1000+	1000+	1000+	1000+	1000+	1000+	1500+	1000+	-
Dielectric Strength kV/mm	D149	12.6	12.6	14	15.8	12.6	13.8	13.8	13.8	14.2	14.2	13.8	13.8	-
PHYSICAL PROPERTIES														
Specific Gravity	D792	1.9-2.0	1.8-2.0	1.7-1.9	1.8-1.9	1.8-1.9	1.8-1.5	1.75-1.8	1.7-1.75	1.85-1.95	1.7-1.85	1.7-1.9	1.75-1.8	1.90-2.05
Mold Shrinkage 0.001/in	D955	0.5-3	0.5-3	0.5-2	0.5-3	0.5-3	0.5-3	0.5-2	0.5-2	0.5-1.5	0.5-1.5	0.5-3	0.5-2	-0.002
Barcol Hardness	D2583	35-50	35-45	45-55	25-35	35-45	35-45	35-45	40-50	45-55	45-55	41-47	35-45	40-60
Heat Distortion Temp @ 264 psi Deg C	D648	>260	>260	>260	>260	>260	>260	>260	>260	>260	>260	>260	>260	>260
Water Absorption % in 24 hrs	D570	0.17	0.17	0.13	0.17	0.14	0.13	0.12	0.13	0.12	0.12	0.12	0.12	0.1-0.3
Bulk Factor	D1895	1	1	3	1	1	1	2	3	1.5	1.5-2	1-1.5	2	-
COLOR CHANGE UNDER HEAT														
White 150°C for 300 hrs, ΔE	-	-	-	-	-	-	-	-	-	1.2-1.7	1.2-1.7	-	-	-
Bisque 150°C for 300 hrs, ΔE	-	-	-	-	-	-	-	-	-	1-1.5	1-1.5	-	-	-

All property values are based on test performed on standard ASTM test samples and according to standard ASTM test methods unless otherwise indicated. This information is offered solely for your consideration and is to be used as a guide only. No other warranty is implied.

Contact Us:

CORPORATE HEADQUARTERS

10095 Queens Way Chagrin Falls, Ohio 44023-5495
 (440) 543-7526 Fax: (440) 543-4691

Revised: 10/29/18